

	TELAS SIN TEJER TEFISA <small>TELAS Y FABRICADOS NO TEJIDOS S.A.</small>	Ctra. Piera-Sant Sadurní, km. 5 08784 PIERA - (Barcelona) - SPAIN TEL. +34 - 93 770 60 60 - FAX +34 - 93 770 60 62 e-mail: tefisa@tefisa.com http://www.tefisa.com	
COMMERCIAL DEPARTMENT - F.5.10 Version: 004	Date: 12/09/2007	Page 1 of 1	
CHARACTERISTICS SHEET			

FC-01250/L9

CHARACTERISTIC	NORM	VALUE	UNITS	TOLERANCE	
				- %	+ %
N.W. WEIGHT	EN 29073-1 = edana 40.3-90	125	gr/m2	10	15
THICKNESS	EN 29073-2 = edana 30.5-99	900	microns	30	30
TENSILE STRENGTH M.D.	EN 29073-3 = edana 20.2-89	> 180	N/5 cm		
TENSILE STRENGTH C.D.	EN 29073-3 = edana 20.2-89	> 55	N/5 cm		
PERMEABILITY TO AIR	UNE EN ISO 9237:1996	2910	l/(m2.seg)		
FLAME RETARDING TEST-1	FAR 25 - 25.853 (b) y apend. F	Test OK			
COLOUR		White			
FIBRE		Viscose			

EDITION	4
APPROVAL DATE	24/01/05

COMMERCIAL DEPARTMENT

The data that appear in this Characteristics Sheet are informative. We reserve the right of modifying them in the future.
 In the event of special applications, we request consult with our Technical Department.