

	TELAS SIN TEJER TEFISA TELAS Y FABRICADOS NO TEJIDOS S.A.	Ctra. Piera-Sant Sadurní, km. 5 08784 PIERA - (Barcelona) - SPAIN TEL. +34 - 93 770 60 60 - FAX +34 - 93 770 60 62 e-mail: tefisa@tefisa.com http://www.tefisa.com	
<h2>CHARACTERISTICS SHEET</h2>			

FF-G100					
CHARACTERISTIC	NORM	VALUE	UNITS	TOLERANCE	
				- %	+ %
N.W. WEIGHT	EN 29073-1 = edana 40.3-90	100	gr/m2	10	15
THICKNESS	EN 29073-2 = edana 30.5-99	1000	microns	30	30
TENSILE STRENGTH M.D.	EN 29073-3 = edana 20.2-89	> 175	N/5 cm		
TENSILE STRENGTH C.D.	EN 29073-3 = edana 20.2-89	> 32	N/5 cm		
WET TENSILE STRENGTH M.D.	EN 29073-3 = edana 20.2-89	> 100	N/5 cm		
WET TENSILE STRENGTH C.D.	EN 29073-3 = edana 20.2-89	> 12	N/5 cm		
PERMEABILITY TO AIR	UNE EN ISO 9237:1996	3180	l/(m2.se g)		
COLOUR		White			
FIBRE		Synthetic			
SUITABLE FOR FOOD PROCESS		Yes (*)			

EDITION	3
APPROVAL DATE	07/07/05

NOTE:

(*) For every end use, compatibility test in working conditions must be done.

COMMERCIAL DEPARTMENT

The data that appear in this Characteristics Sheet are informative. We reserve the right of modifying them in the future. In the event of special applications, we request consult with our Technical Department.