

 TELAS SIN TEJER TEFISA TELAS Y FABRICADOS NO TEJIDOS S.A.	Ctra. Piera-Sant Sadurní, km. 5 08784 PIERA - (Barcelona) - SPAIN TEL. +34 - 93 770 60 60 - FAX +34 - 93 770 60 62 e-mail: tefisa@tefisa.com http://www.tefisa.com	
<h2>CHARACTERISTICS SHEET</h2>		

<h1>FT-1200</h1>					
CHARACTERISTIC	NORM	VALUE	UNITS	TOLERANCE	
				- %	+ %
N.W. WEIGHT	EN 29073-1 = edana 40.3-90	20	gr/m2	10	20
THICKNESS	EN 29073-2 = edana 30.5-99	170	microns	30	30
TENSILE STRENGTH M.D.	EN 29073-3 = edana 20.2-89	> 46	N/5 cm		
TENSILE STRENGTH C.D.	EN 29073-3 = edana 20.2-89	> 8	N/5 cm		
WET TENSILE STRENGTH M.D.	EN 29073-3 = edana 20.2-89	> 28	N/5 cm		
WET TENSILE STRENGTH C.D.	EN 29073-3 = edana 20.2-89	> 4	N/5 cm		
PERMEABILITY TO AIR	UNE EN ISO 9237:1996	5220	l/(m2.se g)		
PERMEABILITY TO WATER	Permeámetro de CA	316	m3/(m2. hora)		
AVERAGE PORE DIAMETER	BS 3321:1986	246	microns		
COLOUR		White			
FIBRE		Viscose/Synthetic			

EDITION	5
APPROVAL DATE	12/01/05

COMMERCIAL DEPARTMENT

The data that appear in this Characteristics Sheet are informative. We reserve the right of modifying them in the future.
 In the event of special applications, we request consult with our Technical Department.