

 <b>TELAS SIN TEJER</b> <b>TEFISA</b> TELAS Y FABRICADOS NO TEJIDOS S.A.	Ctra. Piera-Sant Sadurní, km. 5 08784 PIERA - (Barcelona) - SPAIN TEL. +34 - 93 770 60 60 - FAX +34 - 93 770 60 62 e-mail: tefisa@tefisa.com http://www.tefisa.com	
<h2>CHARACTERISTICS SHEET</h2>		

FT-G100/B					
CHARACTERISTIC	NORM	VALUE	UNITS	TOLERANCE	
				- %	+ %
N.W. WEIGHT	EN 29073-1 = edana 40.3-90	100	gr/m2	10	15
THICKNESS	EN 29073-2 = edana 30.5-99	800	microns	30	30
TENSILE STRENGTH M.D.	EN 29073-3 = edana 20.2-89	> 210	N/5 cm		
TENSILE STRENGTH C.D.	EN 29073-3 = edana 20.2-89	> 40	N/5 cm		
WET TENSILE STRENGTH M.D.	EN 29073-3 = edana 20.2-89	> 160	N/5 cm		
WET TENSILE STRENGTH C.D.	EN 29073-3 = edana 20.2-89	> 25	N/5 cm		
PERMEABILITY TO AIR	UNE EN ISO 9237:1996	1490	l/(m2.se g)		
PERMEABILITY TO WATER	Permeámetro de CA	130	m3/(m2. hora)		
AVERAGE PORE DIAMETER	BS 3321:1986	164	microns		
COLOUR		White			
FIBRE		Synthetic			

EDITION	6
APPROVAL DATE	17/01/05

### COMMERCIAL DEPARTMENT

The data that appear in this Characteristics Sheet are informative. We reserve the right of modifying them in the future. In the event of special applications, we request consult with our Technical Department.